

**PROCESS FOR THE PREPARATION OF CEMENT COMPLEX**

**Publication number:** KR920008773B  
**Publication date:** 1992-10-09  
**Inventor:** PARK SUNG-BOM (KR)  
**Applicant:** PARK SUNG BOM (KR)  
**Classification:**  
- **international:** **C04B14/04; C04B14/02;** (IPC1-7): C04B14/04  
- **European:**  
**Application number:** KR19890017346 19891128  
**Priority number(s):** KR19890017346 19891128

**Report a data error here**

**Abstract of KR920008773B**

A lightweight carbon fiber reinforced cement composite is produced by (1) mixing hydraulic commercial portland cement with silica powder, which is 50-200 m in average particle size, more than 90 % in silica (SiO<sub>2</sub>) content and about 2.60-2.65 in specific gravity, (2) charging in it with PAN based carbon fiber and Pitch based carbon fiber, which are 3-20 mm long, 1.6-1.8 of specific gravity, 7,500-38,000 kgf/cm<sup>2</sup> of tensile strength, 3.5-25.0 kg/cm<sup>2</sup> of elastic coefficient, 6.5-20 [ $\mu$ ]m of diameter, by the volumn ratio of 1.0-5.0 %, (3) changing the water/cement ratio into the range of 20-110 % using thickener additive, antifoaming agent and water reducing agent, (4) operating an autoclave hardening the above mixture at 180 +- 5 deg.C, under 10 atm, for 3-5 hrs.

---

Data supplied from the **esp@cenet** database - Worldwide